

# General Product Information

ROCKWOOL stone wool products are made of basalt, a volcanic stone.

ROCKWOOL stone wool products are non-combustible with a melting point more than 1000°C. They are particularly suitable for thermal insulation, fire protection and sound reduction/absorption.

ROCKWOOL stone wool is inorganic and contains no nutritious substance. Therefore it will not be attacked by microorganisms. Stone wool will not rot and does not attract vermin.

No CFCs, HFCs, HCFCs, or asbestos are used in the manufacture of ROCKWOOL stone wool products.



# ThermalRock B (Blanket)

## Common applications

ThermalRock B is manufactured in a wide variety of thicknesses and densities to suit most requirements, suitable for general application in residential, commercial and industrial buildings.

#### **Dimensions**

Product Type	Thickness (mm)	Length x Width (mm)			
B40	50	5000 x 1200			
	50	7500 x 1200			
B50	50	5000 x 1200			
	50	7500 x 1200			
B60	50	5000 x 1200			
	50	7500 x 1200			
	25	8000 x 1200			
B80	25	10000 x 1200			
	50	5000 x 1200			
	50	7500 x 1200			
B100	25	5000 x 1200			
	25	8000 x 1200			
	50	2500 x 1200			
	50	4000 x 1200			

Note: Please contact your local representatives for the specific densities and thicknesses that are available locally.

#### **Facings**

ThermalRock B products are available in plain, aluminium foil facings and one-sided glass tissue facings.

#### Packaging and storage

ThermalRock B is supplied in folded or roll form (depending on factory) and shrink-wrapped in polyethylene sheets for ease of handling, transportation, storage and identification. Products should be stored indoors or under a waterproof covering.



### **Technical Parameters**

Product Types	B40	B50	B60	B80	B100	Standard
Nominal Density (kg/m³)	40	50	60	80	100	J.a.i.a.i.a
Thermal Conductivity (W/mK)*	0.036	0.035	0.034	0.034	0.035	ASTM C518
Sound Absorption	Please contact your local representative for more information					ISO 354
Fire Performance	Non-	combustible	EN 13501-1			
Water Vapour Absorption (Moisture Resistance)	< 0.04 %, by volume					ASTM C1104/C1104M
Water Absorption (Partial Immersion)	< 1.0 kg/m <sup>2</sup>					EN 1609

<sup>\*</sup> Thermal conductivity is tested at mean temperature of 20°C in accordance with ASTM C518 by external accredited laboratory. It is recommended to have a safety factor of 20% as design value.



www.rockwoolasia.com

ROCKWOOL Malaysia Sdn Bhd Lot 4, Solok Waja 1 Bukit Raja Industrial Estate 41050 Klang, Selangor Malaysia T (+60) 3 3341 3444 F (+60) 3 3342 7290 ROCKWOOL Malaysia Sdn Bhd 175 A&B Kawasan Perindustrian Air Keroh, Jalan Lingkungan Usaha, 75450 Melaka Malaysia T (+60) 6 233 2010 F (+60) 6 233 2012 ROCKWOOL (Thailand) Limited Hemaraj Eastern Industrial Estate (Map Ta Phut) 1 Soi G 2, Pakornsongkrohraj Road, Huaypong, Muang Rayong 21150 Thailand T (+66) 3868 5110 F (+66) 3868 4938 Disclaimer: The information contained in this data sheet is believed to be correct at the date of publication. ROCKWOOL does not accept responsibility for the consequences of using ThermalRock B in applications different from those described above

